

# INVISTA HV240A PA66 Resin

## Product Description

INVISTA HV240A is a high viscosity PA66 resin for extrusion, injection molding, and compounding applications. It is non-lubricated and has excellent whiteness.

	Properties (dry)	Value	Units	Method
VISCOSITY	VN at 0.5% in formic acid, nominal	295	mL/g	ISO 307
	VN at 0.5% in sulfuric acid, nominal	300	mL/g	ISO 307
	RV at 1% in sulfuric acid, nominal	4.6	—	—
	RV in formic acid, nominal	240	—	ASTM D789
PHYSICAL	Density	1.14	g/cm <sup>3</sup>	ISO 1183
	Mold Shrinkage, 2.0 mm, Parallel	1.3	%	ISO 294-4
	Mold Shrinkage, 2.0 mm, Transverse	1.5	%	ISO 294-4
	Water Absorption - 24 hours	1.8	%	ISO 62
	Water Absorption - Equilibrium @ 50% RH	2.7	%	ISO 62
MECHANICAL	Tensile Strength at Yield	84	MPa	ISO 527
	Elongation at Yield	4.2	%	ISO 527
	Elongation at Break	50	%	ISO 527
	Tensile Modulus	3150	MPa	ISO 527
	Flexural Modulus	2900	MPa	ISO 178
	Flexural Strength	100	MPa	ISO 178
	Notched Charpy at 23°C	6.2	kJ/m <sup>2</sup>	ISO 179
	Notched Charpy at -30°C	6.4	kJ/m <sup>2</sup>	ISO 179
	Unnotched Charpy at 23°C	NB	kJ/m <sup>2</sup>	ISO 179
	Unnotched Charpy at -30°C	NB	kJ/m <sup>2</sup>	ISO 179
THERMAL	Notched Izod at 23°C	5.5	kJ/m <sup>2</sup>	ISO 180
	Melting Temperature, 10°C/min	262	°C	ISO 11357
	HDT at 0.45 MPa	206	°C	ISO 75
	HDT at 1.80 MPa	72	°C	ISO 75

	Properties (dry)	Value	Units	Method
ELECTRICAL	Volume Resistivity, 2.0 mm	1010	ohm-cm	UL 746A
	Dielectric Strength, 1.0 mm	10.8	kV/mm	UL 746A
	Comparative Tracking Index, 3.0 mm	≥600	volts	UL 746A
FLAMMABILITY	Flammability Classification at 0.40 mm	HB	—	UL 94
	Flammability Classification at 0.71 mm	HB	—	UL 94
	Flammability Classification at 1.5 mm	V-2	—	UL 94
	Flammability Classification at 3.0 mm	V-2	—	UL 94

## General Information

### Material Status

Commercial: Active

### Availability

- North America
- South America
- Europe
- Asia

### Features

- High viscosity
- Excellent whiteness and processability
- Fast and consistent crystallization

### RoHS

No intentional additives or ingredients used in HV240A are among those in the European directive 2011/65/EC (RoHs), as amended.

## Process Guidelines for Molding

Drying temperature	90 °C
Drying time*	4 - 6 hours
Barrel temperatures	
Rear	250 - 280 °C
Middle	275 - 290 °C
Front	275 - 290 °C
Nozzle	275 - 295 °C
Processing temperature (melt)	280 - 295 °C
Mold temperature	50 - 90 °C
Back pressure**	2 - 10 bar
Vent depth	0.007 - 0.04 mm
Cushion (range)	4 - 6 mm
Suggested moisture (max)	0.03 wt%
Suggested moisture (min)	0.005 wt%
Screw speed	50 - 150 rpm

\* Initial moisture below 0.10 wt%. Use dehumidified air.

\*\* Melt pressure

#### Product Data Sheet Disclaimer

This Product Data Sheet relates only to the identified product and any identified uses. It is based on information available as of April 2021. Additional information may be needed to evaluate other uses of the product, including use of the product in combination with any materials or in any processes other than those specifically referenced. THIS PRODUCT DATA SHEET DOES NOT CONTAIN A COMPLETE STATEMENT OF, AND DOES NOT CONSTITUTE A REPRESENTATION, WARRANTY OR GUARANTY WITH REGARD TO, A PRODUCT'S CHARACTERISTICS, USES, QUALITY, MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR THE SUITABILITY, SAFETY, EFFICACY, HAZARDS OR HEALTH EFFECTS OF THE PRODUCT, WHETHER USED SINGULARLY OR IN COMBINATION WITH ANY OTHER PRODUCT, EXCEPT TO THE EXTENT REQUIRED BY THE RELEVANT LAW AND REGULATIONS. Nothing contained in this Product Data Sheet shall be construed to modify any of the terms under which the product was sold by INVISTA. INVISTA and design are trademarks of INVISTA. ©2021 INVISTA.  
www.nylonpolymer.INVISTA.com