

# INVISTA U4201 PA66 Resin

## Product Description

INVISTA U4201 NC01 is a general purpose, PA66 feedstock resin produced with low viscosity for higher flow. Primary use is compounding.

	Properties (dry)	Value	Units	Method
VISCOSITY	RV in formic acid, nominal	42	—	ASTM D789
	VN at 0.5% in sulfuric acid, nominal	138	mL/g	ISO 307
	RV at 1% in sulfuric acid, nominal	2.55	—	—
PHYSICAL	Density	1.14	g/cm <sup>3</sup>	ISO 1183
	Mold Shrinkage, 2.0 mm, Parallel	1.4	%	ISO 294-4
	Mold Shrinkage, 2.0 mm, Transverse	1.4	%	ISO 294-4
	Water Absorption - 24 hours	1.8	%	ISO 62
	Water Absorption - Equilibrium @ 50% RH		%	ISO 62
MECHANICAL	Tensile Strength at Yield	82	MPa	ISO 527
	Elongation at Yield	4.4	%	ISO 527
	Elongation at Break	33	%	ISO 527
	Tensile Modulus	2800	MPa	ISO 527
	Flexural Modulus	2800	MPa	ISO 178
	Flexural Strength	92	MPa	ISO 178
	Notched Charpy at 23°C	5.0	kJ/m <sup>2</sup>	ISO 179
	Notched Charpy at -30°C	4.3	kJ/m <sup>2</sup>	ISO 179
	Unnotched Charpy at 23°C	NB	kJ/m <sup>2</sup>	ISO 179
	Unnotched Charpy at -30°C	260	kJ/m <sup>2</sup>	ISO 179
	Notched Izod at 23°C	3.8	kJ/m <sup>2</sup>	ISO 180
THERMAL	Melting Temperature, 10°C/min	258	°C	ISO 11357
	HDT at 0.45 MPa	191	°C	ISO 75
	HDT at 1.80 MPa	62	°C	ISO 75

## General Information

### Material Status

Commercial: Active

### Availability

- North America
- South America
- Europe
- Asia

### Features

- High flow for ease of processing
- Stable low viscosity
- Good whiteness

### RoHS

No intentional additives or ingredients used in U4201 are among those in the European directive 2011/65/EC (RoHs), as amended.

## Process Guidelines for Molding

Drying temperature	80 °C
Drying time*	8 - 12 hours
Barrel temperatures	
Rear	250 - 270 °C
Middle	270 - 290 °C
Front	270 - 290 °C
Nozzle	270 - 290 °C
Processing temperature (melt)	280 - 295 °C
Mold temperature	50 - 90 °C
Back pressure**	2 - 10 bar
Vent depth	0.007 - 0.04 mm
Cushion (range)	4 - 6 mm
Suggested moisture (max)	0.20 wt%
Suggested moisture (min)	0.10 wt%
Screw speed	75 - 180 rpm

\* Initial moisture below 0.5 wt%. Use dehumidified air.

\*\* Melt pressure

#### Product Data Sheet Disclaimer

This Product Data Sheet relates only to the identified product and any identified uses. It is based on information available as of April 2021. Additional information may be needed to evaluate other uses of the product, including use of the product in combination with any materials or in any processes other than those specifically referenced. THIS PRODUCT DATA SHEET DOES NOT CONTAIN A COMPLETE STATEMENT OF, AND DOES NOT CONSTITUTE A REPRESENTATION, WARRANTY OR GUARANTY WITH REGARD TO, A PRODUCT'S CHARACTERISTICS, USES, QUALITY, MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR THE SUITABILITY, SAFETY, EFFICACY, HAZARDS OR HEALTH EFFECTS OF THE PRODUCT, WHETHER USED SINGULARLY OR IN COMBINATION WITH ANY OTHER PRODUCT, EXCEPT TO THE EXTENT REQUIRED BY THE RELEVANT LAW AND REGULATIONS. Nothing contained in this Product Data Sheet shall be construed to modify any of the terms under which the product was sold by INVISTA. INVISTA and design are trademarks of INVISTA. ©2021 INVISTA.  
[www.nylonpolymer.INVISTA.com](http://www.nylonpolymer.INVISTA.com)